

# Document made available under the Patent Cooperation Treaty (PCT)

International application number: PCT/US05/009677

International filing date: 24 March 2005 (24.03.2005)

Document type: Certified copy of priority document

Document details: Country/Office: US  
Number: 60/556,250  
Filing date: 25 March 2004 (25.03.2004)

Date of receipt at the International Bureau: 26 September 2005 (26.09.2005)

Remark: Priority document submitted or transmitted to the International Bureau in compliance with Rule 17.1(a) or (b)



World Intellectual Property Organization (WIPO) - Geneva, Switzerland  
Organisation Mondiale de la Propriété Intellectuelle (OMPI) - Genève, Suisse

1369465

# THE UNITED STATES OF AMERICA

TO ALL TO WHOM THESE PRESENTS SHALL COME:

UNITED STATES DEPARTMENT OF COMMERCE

United States Patent and Trademark Office

*September 16, 2005*

**THIS IS TO CERTIFY THAT ANNEXED HERETO IS A TRUE COPY FROM THE RECORDS OF THE UNITED STATES PATENT AND TRADEMARK OFFICE OF THOSE PAPERS OF THE BELOW IDENTIFIED PATENT APPLICATION THAT MET THE REQUIREMENTS TO BE GRANTED A FILING DATE.**

**APPLICATION NUMBER: 60/556,250**

**FILING DATE: *March 25, 2004***

**RELATED PCT APPLICATION NUMBER: *PCT/US05/09677***



Certified by

Under Secretary of Commerce  
for Intellectual Property  
and Director of the United States  
Patent and Trademark Office

17169 U.S. PTO  
032504

PTO/SB/16 (01-04)  
Approved for use through 07/31/2006. OMB 0651-0032  
U.S. Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE  
Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

**PROVISIONAL APPLICATION FOR PATENT COVER SHEET**

This is a request for filing a PROVISIONAL APPLICATION FOR PATENT under 37 CFR 1.53(c).

Express Mail Label No. EV 356 830 877 US

22 54 U.S. PTO  
60/556250  
032504

INVENTOR(S)					
Given Name (first and middle [if any])		Family Name or Surname		Residence (City and either State or Foreign Country)	
James M.		Tour		Bellaire, Texas	
Additional inventors are being named on the _____ separately numbered sheets attached hereto					
TITLE OF THE INVENTION (500 characters max)					
Direct all correspondence to: CORRESPONDENCE ADDRESS					
<input type="checkbox"/> Customer Number: _____					
OR					
<input checked="" type="checkbox"/> Firm or Individual Name Ross Spencer Garsson					
Address Winstead Sechrest & Minick P.C.					
Address P.O. Box 50784					
City Dallas		State TX		Zip	75201
Country U.S.A.		Telephone 512.370.2870		Fax	512.370.2850
ENCLOSED APPLICATION PARTS (check all that apply)					
<input checked="" type="checkbox"/> Specification Number of Pages 9		<input type="checkbox"/> CD(s), Number _____			
<input checked="" type="checkbox"/> Drawing(s) Number of Sheets 3		<input checked="" type="checkbox"/> Other (specify) Check and Postcard			
<input type="checkbox"/> Application Data Sheet. See 37 CFR 1.76					
METHOD OF PAYMENT OF FILING FEES FOR THIS PROVISIONAL APPLICATION FOR PATENT					
<input checked="" type="checkbox"/> Applicant claims small entity status. See 37 CFR 1.27.				FILING FEE	
<input checked="" type="checkbox"/> A check or money order is enclosed to cover the filing fees.				Amount (\$)	
<input checked="" type="checkbox"/> The Director is hereby authorized to charge filing fees or credit any overpayment to Deposit Account Number: 23-2426				80.00	
<input type="checkbox"/> Payment by credit card. Form PTO-2038 is attached.					
The invention was made by an agency of the United States Government or under a contract with an agency of the United States Government.					
<input type="checkbox"/> No. National Science Foundation Grant No. DMR-0073046; University of Washington (AFSOR) Grant No. F49620-01-1-0364; TAMU/TEES, Grant No. NASA NCC-01-0203; National Aeronautics & Space Admin. Grant No. JSC-NCC-9-77; and Office of Naval Research Grant No. N00014-02-1-0752.					
<input checked="" type="checkbox"/> Yes, the name of the U.S. Government agency and the Government contract number are: _____					

Respectfully submitted,

[Page 1 of 2]

Date March 25, 2005

SIGNATURE

REGISTRATION NO. 38,150

(if appropriate)

TYPED or PRINTED NAME Ross Spencer Garsson

Docket Number: 11321-P086V1

TELEPHONE (512) 370-2870

**USE ONLY FOR FILING A PROVISIONAL APPLICATION FOR PATENT**

This collection of information is required by 37 CFR 1.51. The information is required to obtain or retain a benefit by the public which is to file (and by the USPTO to process) an application. Confidentiality is governed by 35 U.S.C. 122 and 37 CFR 1.14. This collection is estimated to take 8 hours to complete, including gathering, preparing, and submitting the completed application form to the USPTO. Time will vary depending upon the individual case. Any comments on the amount of time you require to complete this form and/or suggestions for reducing this burden, should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, U.S. Department of Commerce, P.O. Box 1450, Alexandria, VA 22313-1450. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Mail Stop Provisional Application, Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450.

If you need assistance in completing the form, call 1-800-PTO-9199 and select option 2.

**PROVISIONAL APPLICATION COVER SHEET**  
**Additional Page**

PTO/SB/16 (08-03)

Approved for use through 07/31/2006. OMB 0651-0032

U.S. Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

**Docket Number** 11321-P086V1

INVENTOR(S)/APPLICANT(S)		
Given Name (first and middle [if any] )	Family or Surname	Residence (City and either State or Foreign Country)
Jared L.	Hudson	Houston, Texas
Christopher A.	Dyke	Houston, Texas

[Page 2 of 2]

Number 1 of 1

**WARNING:** Information on this form may become public. Credit card information should not be included on this form. Provide credit card information and authorization on PTO-2038.

**FUNCTIONALIZATION OF CARBON NANOTUBES IN SUPER ACID MEDIUM**

This work was supported by the National Science Foundation, Grant Number DMR-0073046; University of Washington (pass through from AFSOR, Grant Number F49620-01-1-0364); TAMU/TEES, Grant Number NASA NCC-01-0203; National Aeronautics and Space Administration, Grant number JSC-NCC-9-77; and Office of Naval Research, Grant Number N00014-02-1-0752.

**Description of the Invention**

**General Purpose.** The present invention is directed to processes that exploit the solubility of carbon nanotubes in super acid media (*e.g.*, oleum = fuming sulfuric acid =  $\text{H}_2\text{SO}_4$  plus  $\text{SO}_3$ ) to covalently attach functional groups to the sidewalls of carbon nanotubes. This affords individual functionalized carbon nanotubes that are dispersible in a variety of matrices. Such solubility of carbon nanotubes in super acid media is described in PCT Patent Application Publication No. WO 01/30694 A1 by Smalley *et al.* and United States Patent Application Publication No. US 2003/0170166 A1 by Smalley *et al.* Such materials are likely to provide optimal properties in many potential materials applications.

**Technical Description.** While the making and/or using of various embodiments of the present invention are discussed below, it should be appreciated that the present invention provides many applicable inventive concepts that may be embodied in a variety of specific contexts. The specific embodiments discussed herein are merely illustrative of specific ways to make and/or use the invention and do not delimit the scope of the invention.

Purified single wall carbon nanotubes (0.050 g, 4.2 mmol), (prepared according to Chiang, I. W.; Brinson, B. E.; Huang, A. Y.; Willis, P. A.; Bronikowski, M. J.; Margrave, J. L.; Smalley, R. E.; Hauge, R. H. *J. Phys. Chem. B* 2001, 105, 8297) were dispersed in oleum (50 mL, 20% free  $\text{SO}_3$ ) at 80 °C. This dispersion was then filtered over glass wool to remove any large particulate. Sulfanilic acid (2.91 g, 16.8 mmol) was added to the dispersion followed by

sodium nitrite (1.16 g, 16.8 mmol). Finally 2,2'-azo-*bis*-isobutyronitrile (1.38 g, 8.4 mmol) was added to provide a radical source. This solution was allowed to stir at 80 °C for one hour at which point the reaction mixture was poured into 300 mL of water. This mixture was then filtered over a polycarbonate membrane filter (1 µm pore size), and washed with 500 mL of acetone. The resultant black powder, **1**, was then dispersed in water and filtered to be certain any soluble impurities are removed. At this point the material is ready for use or characterization.

Note the attached file of the Raman spectrum (Fig. 1) and the UV/Vis spectrum (Fig. 2) of **1** where the transitions are clear that functionalization has occurred. Most importantly, however, notice the atomic force microscopy (AFM) image (Fig. 3) and corresponding section analysis (Fig. 4) of **1** where many single tubes are formed and they do not tend to re-rope. This material was not centrifuged prior to imaging, and there is no surfactant present. For a description of the spectral characterization utilization, see: Bahr, J. L.; Tour, J. M. "Covalent Chemistry of Single-Wall Carbon Nanotubes—A Review," *J. Mater. Chem.* 2002, *12*, 1952-1958. And for non-bundling tubes, generated by surfactant wrapping followed by functionalization, see: Dyke, C. A.; Tour, J. M. "Unbundled and Highly Functionalized Carbon Nanotubes from Aqueous Reactions," *Nano Lett.* 2003, *3*, 1215-1218; and Dyke, C. A.; Tour, J. M. "Overcoming the Insolubility of Carbon Nanotubes through High Degrees of Sidewall Functionalizing," *Chem. Eur. J.* 2004, *10*, 812-817.

Interestingly, and significantly, when sulfanilic acid was used as described, stable water suspensions of the functionalized nanotubes could be generated. The suspensions did not settle even after one week.

**Utility.** The most immediate and obvious use of this procedure is the production of individual carbon nanotubes by a process that is highly scaleable. It is widely accepted that individual carbon nanotubes are necessary to achieve optimum properties in many potential applications. To date, no process exists to reliably produce individual carbon nanotubes on a bulk scale. The present invention eliminates the need for using fluorine, sonication, and centrifugation which previous methods for generating individual carbon nanotubes have relied upon (a). Fluorine use, sonication and centrifugation are frowned upon heavily by industry due to the difficulty in scaling these processes. Furthermore, the present invention eliminates the use of surfactant-

wrapping of carbon nanotubes followed by sonication and centrifugation (b). Both methods (a) and (b) could never be scaled to provide a process that affords individualized nanotubes in the quantities needed for materials applications in bulk. The protocol disclosed here eliminates the need for centrifugation and wrapping, and it capitalizes on the use of Rice-patented protocols on diazonium functionalization by simply providing a solvent change for the reaction medium. See PCT Patent Application Publication No. WO 02/060812 A2 by Tour *et al.*; PCT Patent Application No. US03/22072 by Tour *et al.*; Bahr *et al.*, "Functionalization of Carbon Nanotubes by Electrochemical Reduction of Aryl Diazonium Salts: A Bucky Paper Electrode," *J. Am. Chem. Soc.*, 123:6536-6542 (2001); and Dyke *et al.*, "Solvent-Free Functionalization of Carbon Nanotubes," *J. Am. Chem. Soc.*, 125:1156-1157 (2003).

**Novelty.** Presently, no other method exists to functionalize single wall carbon nanotubes using a super acid solvent.

**Steps Involved.** In some embodiments, the invention is a process involving the following steps:

1. Oxidatively treated single wall carbon nanotubes are dispersed with stirring in oleum to form a dispersion/solution.
2. The dispersion/solution is filtered over glass wool to remove any impurities.
3. An aniline of choice is added to form a reaction mixture.
4. Sodium nitrite followed by a radical source is then added cautiously to the reaction mixture.
5. The mixture is heated and stirred for one hour.
6. The mixture is diluted with water, filtered, and washed with acetone.
7. The resultant solid (functionalized single wall carbon nanotubes) is suspended in water and filtered again to remove impurities.

**Variations.** Such processes are applicable to other carbon nanotubes such as multi-wall carbon nanotubes. The super acid used in this example is oleum but the process is by no means limited to this medium. Chlorosulfonic and triflic acid are examples of other readily available super acids which would be viable alternatives to oleum. Sulfanilic acid is the aniline used in the above example but any aniline is a possible variation. Under the conditions here, using sulfanilic acid or other anilines that might sulfonate, water soluble nanotubes are yielded. In this particular example 2,2'-azo-bis-isobutyronitrile was used as a radical source. Any substance that is known to break down into radicals at relatively low temperatures may be used as a substitute such as benzoyl peroxide and di-tert-butylperoxide. The addition of radical source may not be essential, but it is desirable. It may be that only small amounts of super acid are needed, such as super acid sufficient to merely make a paste of the mixture, following the protocol of our previously disclosed solvent-free (solvent-wetted) disclosures. See PCT Patent Application No. US03/22072 by Tour *et al.* One could use the pre-formed diazonium salt as well as the aniline/nitrite (alkyl nitrite or sodium nitrite) combinations disclosed here.

There are several other variations that are notable that make this procedure more general.

- (A) Concentration. The concentration of the reaction can vary widely from fractions of a milligram of nanotubes per mL of super acid to paste-like conditions wherein the mechanical action of a stirring system on the super acid-wetted tubes results in exfoliation and reaction of individual nanotubes with the reactant. For a complete description of solvent-wetted reactions or paste-like conditions, see: Dyke, C. A.; Tour, J. M. "Solvent-Free Functionalization of Carbon Nanotubes," *J. Am. Chem. Soc.*, 2003, 125, 1156-1157.
- (B) In addition to the diazonium reactions described previously, this process should be general to a host of organic and organometallic reactions provided that the reagents are sufficiently reactive in the super acid medium for a sufficiently long time for the reaction to take place. Below is a partial list of the reactions that could be possible. For example, use of:
  - a. Cationic intermediates should cause reaction with the nanotubes. For example, use of isopropanol should cause the isopropyl cation to form that would react with the pi-electron rich nanotubes since the nanotubes are the only nucleophilic



species in solution. Likewise, cations can be generated from any alkene or alkyne. Generally, these could be termed Friedel-Crafts-type reactions where the nanotube acts as the nucleophile toward an electrophilic species. The electrophiles could be:

- i. carbocations such as alkyl, alkenyl, alkynyl, aryl, aceyl ( $\text{RCO}^+$ ) cations
  - ii. halonium ions such as  $\text{Cl}^+$ ,  $\text{Br}^+$ ,  $\text{I}^+$  or  $\text{F}^+$  species
  - iii. metal cations, specifically transition metals and group III-A through VI-A metals.
  - iv. Other known types of species used in Friedel-Crafts reactions
- b. Dipolorophiles should be amenable to this reactions such as the Prato dipolorophile reaction (Georgakilas, V.; Kordatos, K; Prato, M.; Guldi, D. M.; Holzinger, M.; Hirsch, A. *J. Am. Chem. Soc.* 2002, *124*, 760.) or nitrile oxide reaction (Meier, M. S.; Poplawska, M. *J. Org. Chem.* 1993, *58*, 4524.) or trimethylene methane-derivatives. Also, ylides should be useable in this process.
- c. Benzyne addition (from anthranilic acid and isoamyl nitrite) (Meier, M. S.; Wang, G.-W.; Haddon, R. C.; Brock, C. P.; Lloyd, M. A.; Selegue, J. P. *J. Am. Chem. Soc.* 1998, *120*, 2337) or 2-(trimethylsilyl)phenyltrifluoro-methanesulfonate treated with TBAF, which has been shown to give benzyne (Himeshima, Y.; Sonoda, T.; Kobayashi, H. *Chem. Lett.* 1983, 1211).
- d. Radical reactions, in general. Radical intermediates can be generated thermally, photochemically or chemically using initiators or sensitizers and this chemistry is compatible with super acid. So any radical source should have a possibility of adding to the nanotubes. This includes:
- i. Carbon radicals such as alkyl, alkenyl, alkynyl, aryl, aceyl ( $\text{RCO}^\cdot$ ) radicals
  - ii. halogen radical species
  - iii. heter-atom radical species such as oxy radicals
  - iv. metal-based radicals, specifically transition metals and group III-A through VI-A metals.

- e. Oxidation reactions such as reaction with
    - i. peroxyacids
    - ii. metal oxidants such as osmium tetroxide, potassium permanganate, chromates
    - iii. ozone
    - iv. oxone
    - v. oxygen
    - vi. superoxides
  - f. Reductants such electrochemical reductants or other species that are super acid-compatible.
  - g. Heteroatomic nucleophiles where the nucleophile bears a lone pair of electrons such as sulfides or thiols.
  - h. Carbenes.
  - i. Dienes that could react with the tubes such that the tubes act as a dieneophile in a Diels-Alder Reaction.
- (C) The process disclosed here used heat, but room temperature processes are also effective on other anilines.
- (D) Other anilines used successfully to date are aniline (aminobenzene) which sulfonates under the same reaction conditions, 2-(4'-aminophenyl)ethanol, 4-chloroaniline, 4-iodoaniline, 4-tert-butylaniline, and 4-nitroaniline. This shows the generality of the process.
- (E) Although the nanotubes used here were oxidatively treated to purify the sample, this protocol can also be used on the crude, as provided nanotubes.

All patents and publications referenced herein are hereby incorporated by reference. It will be understood that certain of the above-described structures, functions, and operations of the above-described embodiments are not necessary to practice the present invention and are included in the description simply for completeness of an exemplary embodiment or

embodiments. In addition, it will be understood that specific structures, functions, and operations set forth in the above-described referenced patents and publications can be practiced in conjunction with the present invention, but they are not essential to its practice. It is therefore to be understood that the invention may be practiced otherwise than as specifically described without actually departing from the spirit and scope of the present invention as defined by the appended claims.

## WHAT IS CLAIMED IS:

1. A method comprising the steps of:
  - a) dispersing single-wall carbon nanotubes in a super acid medium to form a dispersion;
  - b) adding aniline species and sodium nitrite to the dispersion to form a reaction mixture; and
  - c) reacting the reaction mixture to form functionalized single-wall carbon nanotubes.
2. The method of Claim 1, wherein the single-wall carbon nanotubes have been oxidatively treated.
3. The method of Claim 1 or 2, wherein the single-wall carbon nanotubes are homogeneous in a characteristic selected from the group consisting of length, diameter, chirality, and combinations thereof.
4. The method of Claims 1-2, or 3 further comprising a step of filtering the dispersion to remove any large particles.
5. The method of Claims 1-3, or 4, wherein the super acid medium is selected from the group consisting of oleum, chlorosulfonic acid, triflic acid, and combinations thereof.
6. The method of Claims 1-4, or 5, wherein the aniline species comprises sulfanilic acid.
7. The method of Claims 1-5, or 6 further comprising a step of adding a radical source to the reaction mixture.
8. The method of Claim 7, wherein the radical source is selected from the group consisting of 2,2'-azo-bis-isobutyronitrile, benzoyl peroxide, di-tert-butylperoxide, and combinations thereof.
9. The method of Claims 1-7, or 8, wherein the step of reacting comprises heating and stirring.
10. The method of Claims 1-8, or 9 further comprising the steps of:
  - a) diluting the reaction mixture with water, subsequent to forming functionalized single-wall carbon nanotubes, to form a diluted reaction product mixture;

- b) filtering the diluted reaction product mixture over a filter to isolate the functionalized single-wall carbon nanotubes; and
  - c) washing the isolated functionalized single-wall carbon nanotubes with a washing solvent to obtain washed functionalized single-wall carbon nanotubes.
11. The method of Claim 10, wherein the washing solvent is acetone.
12. The method of Claim 10 or 11 further comprising the steps of:
- a) re-suspending the washed functionalized single-wall carbon nanotubes in water to form a re-suspension;
  - b) filtering the re-suspension to recover re-washed functionalized single-wall carbon nanotubes.

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**



Defective images within this document are accurate representations of the original documents submitted by the applicant.


Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.**

*Fig. 1**Fig. 2*




mjc20040225fc.006

AFM image of 1 showing many individual functionalized single-wall carbon nanotubes.

*Fig. 3*





AFM image of 1 showing an individual nanotube section analysis.

*Fig. 4*